






FIRE BLOCKER (woven)

TECHNICAL DATA

COMPOSITION	93% Meta-Aramid, 5% Para-Aramid, 2% Antistatic
ARTICLE	6001 - Fire Blocker 110
WEIGHT (g/m ²)	110 (±5%)
WIDTH (cm)	min. 160
CONSTRUCTION	1/1 Plain Ripstop
TENSILE STRENGTH EN ISO 13934-1	Warp > 600 N Weft > 600 N
TEAR STRENGTH EN ISO 13937-2	Warp > 25 N Weft > 25 N
ABRASION RESISTANCE EN ISO 12947-2 (9kPa)	> 30000 cycle
DIMENSIONAL CHANGE ISO 6330/ISO 5077	< %3

Natural Finish, Water Repellant Finish or Wicking Finish Available

PROTECTION LEVEL

 HEAT AND FLAME PROTECTION EN ISO 11612	A1, A2
 ELECTROSTATIC PROTECTION EN 1149-3 & EN 1149-5	PASS
 FIREFIGHTING PROTECTION EN 469	N/A
 WILDLAND FIREFIGHTING PROTECTION EN 15384	N/A
 LIQUID CHEMICALS EN 13034	N/A

CLEANING INSTRUCTIONS



Colours

Dark Blue



AKATEK