






# ECO-LINER (woven)

## TECHNICAL DATA

COMPOSITION	55% Modacrylic, 25% Modal, 15% Aramid, 5% FR PA 6.6
ARTICLE	6003 - Eco-Liner 120
WEIGHT (g/m <sup>2</sup> )	120 (±5%)
WIDTH (cm)	min. 160
CONSTRUCTION	1/1 Plain
TENSILE STRENGTH EN ISO 13934-1	Warp > 350 N Weft > 250 N
TEAR STRENGTH EN ISO 13937-2	Warp > 20 N Weft > 20 N
ABRASION RESISTANCE EN ISO 12947-2 (9kPa)	> 30000 cycle
DIMENSIONAL CHANGE ISO 6330/ISO 5077	< %3

Natural Finish, Water Repellant Finish or Wicking Finish Available

## PROTECTION LEVEL

 HEAT AND FLAME PROTECTION EN ISO 11612	A1, A2**
 ELECTROSTATIC PROTECTION EN 1149-3 & EN 1149-5	N/A
 FIREFIGHTING PROTECTION EN 469	PASS**
 WILDLAND FIREFIGHTING PROTECTION EN 15384	N/A
 LIQUID CHEMICALS EN 13034	N/A

\* With Water Repellant Finish Only


\*\* Tested After 50 Industrial Washes

## CLEANING INSTRUCTIONS



## Colours

Grey



# AKATEK