






KAMA (woven)

TECHNICAL DATA

| | |
|---|---|
| COMPOSITION | 58% Para-Aramid, 40% Meta-Aramid, 2% Antistatic |
| ARTICLE | 507 - Kama W 215 |
| WEIGHT (g/m ²) | 215 (±5%) |
| WIDTH (cm) | 160 (±2) |
| CONSTRUCTION | Special Panama |
| TENSILE STRENGTH EN ISO 13934-1 | Warp > 1400 N Weft > 1900 N |
| TEAR STRENGTH EN ISO 13937-2 | Warp > 100 N Weft > 110 N |
| ABRASION RESISTANCE EN ISO 12947-2 (12kPa) | > 35000 cycle |

Natural Finish, Water Repellant Finish or Wicking Finish Available

PROTECTION LEVEL

| | |
|--|--------------------|
|  HEAT AND FLAME PROTECTION EN ISO 11612 | A1, A2, B1, C1, F1 |
|  ELECTROSTATIC PROTECTION EN 1149-3 & EN 1149-5 | PASS** |
|  FIREFIGHTING PROTECTION EN 469 | PASS** |
|  WILDLAND FIREFIGHTING PROTECTION EN 15384 | PASS** |
|  LIQUID CHEMICALS EN 13034 | PASS* |

* With Water Repellant Finish Only

** Tested After 50 Industrial Washes

CLEANING INSTRUCTIONS



Colours

Dark Blue

Gold



AKATEK