







MACO-S (woven)

TECHNICAL DATA

COMPOSITION	60% Modacrylic, 38% Cotton, 2% Antistatic
ARTICLE	374 - Maco-S W 250
WEIGHT (g/m ²)	250 (±5%)
WIDTH (cm)	160 (±2)
CONSTRUCTION	2/1 Twill
TENSILE STRENGTH EN ISO 13934-1	Warp > 700 N Weft > 500 N
TEAR STRENGTH EN ISO 13937-2	Warp > 15 N Weft > 15 N
ABRASION RESISTANCE EN ISO 12947-2 (12kPa)	> 20000 cycle

Natural Finish, Water Repellant Finish or Wicking Finish Available

PROTECTION LEVEL

 HEAT AND FLAME PROTECTION ISO 11612	A1, A2, B1, C1, E2, F1
 ELECTROSTATIC PROTECTION EN 1149-3 & EN 1149-5	PASS
 ELECTRIC ARC PROTECTION (BOX TEST) EN 61482-2	APC 1 (4kA)
 ELECTRIC ARC PROTECTION (OPEN ARC) EN 61482-2	ATPV 9,5 cal/cm ²
 WELDING PROTECTION EN ISO 11611	Class 1
 LIQUID CHEMICALS EN 13034	PASS*

* With Water Repellant Finish Only

CLEANING INSTRUCTIONS



Colours

Dark Blue

Royal Blue

Red

Black

Orange

Dark Grey

Hi-Vis Yellow



AKATEK