

3D MOISTURE BARRIER

TECHNICAL DATA

COMPOSITION	Heat Resistant 3D Spunlaced Nonwoven 67% Meta-Aramid, 33% Para-Aramid Laminated to a Membrane	
ARTICLE	4003 - Moisture Barrier 165 (e-PTFE Bicomponent)	4008 - Moisture Barrier 165 (PU)
WEIGHT (g/m ²)	165 (±5%)	165 (±5%)
WIDTH (cm)	min. 150	min. 150
HEAT RESISTANCE 180 °C ISO 17493	PASS	PASS
TENSILE STRENGTH ISO 9073-3	Lengthwise 400 N Crosswise 250 N	Lengthwise 400 N Crosswise 250 N
TEAR STRENGTH EN ISO 9073-4	Lengthwise 350 N Crosswise 200 N	Lengthwise 350 N Crosswise 200 N
RESISTANCE TO WATER PENETRATION ISO 811	> 100 kPa	> 100 kPa

CLEANING INSTRUCTIONS



Colours



AKATEK